



SUPPLEMENTARY EU-TYPE EXAMINATION CERTIFICATE

Component Intended for use on/in an Equipment or Protective System, Intended for use in Potentially Explosive Atmospheres
Directive 2014/34/EU

Supplementary EU-Type Examination Certificate Number **LOM 14ATEX3028U/4** issue **0**

Product Empty boxes
Serie GEOEX, types GEO...EX

Manufacturer Delvalle Global Solutions, S.L.U.

Address Paso El Prao, 6
01320 – Oyón - Alava
SPAIN

This supplementary certificate extends EC Type Examination Certificate No. LOM 14ATEX3028U to apply to products designed and constructed in accordance with the specification set out in the Schedule of the said certificate but having any variations specified in the Schedule attached to this certificate and the documents therein referred to.

Laboratorio Oficial J.M. Madariaga (LOM), Notified Body number 0163 in accordance with Article 17 of Directive 2014/34/EU of the European Parliament and of the Council, dated 26 February 2014, certifies that the product, as modified by this supplementary certificate, has been found to comply with the Essential Health and Safety Requirements relating to the design and construction of products intended for use in potentially explosive atmospheres given in Annex II to the Directive

In accordance with Article 41 of Directive 2014/34/EU, EC-Type Examination Certificates referring to 94/9/EC that were in existence prior to the date of application of 2014/34/EU (20 April 2016) may be referenced as if they were issued in accordance with Directive 2014/34/EU. Supplementary Certificates to such EC-Type Examination Certificates, and new issues of such certificates, may continue to bear the original certificate number issued prior to 20 April 2016.

Getafe,
Digitally signed by:

Certification Committee



LABORATORIO OFICIAL J. M. MADARIAGA

13 SCHEDULE

14 Supplementary EU-Type Examination Certificate Number **LOM 14ATEX3028U/4**

15 Description of the variation to the Product

Two new types of silicone gaskets are included:

Additional service temperature for spongy silicone gasket: -45 °C a 135 °C

Additional service temperature for injected silicone gasket: -45 °C a 150 °C

Update to the standard EN 60079-7:2015.

Update of the marking label and documentation.

Changes in marking:



II 2G

II 2D

Ex eb IIC Gb

Ex tb IIIC Db IP66

16 Report Number **18.251Z**

17 Schedule of Limitations

Without changes

18 Essential Health and Safety Requirements

Without changes

19 Documents and drawings

Number	sheet	Issue	Date	Description
PV1617JUNSIL	31	1	2017-01-31	Technical dossier
IT.GEO.IECEX	18	v.2	2019-01-10	Instructions manual